

CIA. SIDERURGICA DE CALIFORNIA, S.A. DE C.V.

MATRIZ:

PLANTA GUADALAJARA

SUCURSAL:

AV. LAZARO CARDENAS No. 601

EDIF. "A" 3º PISO

COLONIA LA NOGALERA

TEL: (01-33) 36-69-57-57 FAX: 38-11-82-02

C.P. 44440 GUADALAJARA, JALISCO, MEXICO.

LOTES 1 Y 2 INT. "A" COLONIA COLORADO No. 4

DELEGACION CERRO PRIETO

TELS:(01-686) 5-62-89-89 Y 58 FAX: 5-62-02-91

APDO. POSTAL 9-12 Y 9-14 MEXICALI

P.O.BOX 872-197 CALEXICO, CA. 92232

C.P. 21030 MEXICALI, B.C., MEXICO.

Certificado de Calidad Quality Certificate

No REMISION
PACKING LIST No

25727

FECHA
DATE

26/05/2005

HORA
TIME

10:42:48

No.CLIENTE
CUSTOMER No.

28657

ALMACEN
BRANCH

41827

R55370001

SOLID TO:
VENDIDO A:

PLESA ANAHUAC Y CIAS, S.A. DE C.V.

AV. VALLE DE LAS ALAMEDAS N.66-O
COL. SAN FRANCISCO CHILPAN
TULTITLAN EM CP:54940

MEX

RFC:PAC-040303-UY6

ENVIADO A:
SHIP TO:

PLESA ANAHUAC Y CIAS, S.A. DE C.V.
AV. VALLE DE LAS ALAMEDAS N.66-O

COL. SAN FRANCISCO CHILPAN
TULTITLAN EM CP:54940

MEX

RFC:PAC-040303-UY6

CONSIGNAR A:
C.BROKER:

TRANSPORTE
SHIP VIA

9830

Transportista Dummy Terrestre

No.GUIA
SHIPMENT No.

1431

No.PLACAS
LOC.PLATES

927 DB4

O/E
?

E

USUARIO
USER

JACASTILLO

ANALISIS QUIMICOS/CHEMICAL ANALYSIS

COLADA HEAT	Grado de Acero	%P	%S	%Sn	%C	%Cu	%Mo	%Si	%Ni	%Cr	%V	%Mn	%Nb	%Ti	C.Es	I.G.
362022	ASTM A36	.011	.033	.010	.190	.260	.019	.220	.090	.080	.001	.630	.001	.002		

ANALISIS MECANICOS Y FISICOS/MECHANICAL AND PHYSICAL PROPERTIES

COLADA HEAT	Norma de Fabricacion Product Specification	Lim.Elast. Yield Strength (Lb/In2)	Esf.Max. Tensile Strength (Lb/In2)	Elong. (%)	Dureza Hardness	Estructura Estructure	Inclusiones Cleaness	Tamaño Grano Grain Size	Descarbur.	Doblez	Rec/Oval.
362022	ASTM A6/A 6M-94a	50,192	71,950	27							


COLADA
HEAT

Producto
Item

362022 CUAD 1/2 A36 12.7MM

Atados por Colada
Bundles by Heat

SFE03749 SFE03750



ASEGURAMIENTO DE CALIDAD