Bill To: SIDERTUL SA DE CV RFC# SID930918KR0 AVENIDA PRESIDENTE MASARYK MEXICO CITY DF

Ship To: 7 SIDERTUL SA DE CV 402 GRAND CENTRAL BLVD MILO DISTRIBUTION CENTER LAREDO

Order Date:06/17/2011 PO No:4500012651 Mill Order No:3899438 Load No:1394670 Manifest No:2092137

CERTIFIED MATERIAL TEST REPORT GERDAU AMERISTEEL

G GERDAU AMERISTEEL

Midlothian Mill 300 Ward Road Midlothian, TX 76065 (972)775-8241

MΧ

SIZE W 21 X 68# / W530 X 101

78045

GRADE 992/572-50

TX

US

LENGTH 40 FT / 12.192 M PRODUCT WF BEAMS

HEAT NO: 22606070

11570

SPECIFICATIONS ASTM A6-09, A992-06a, A572-07

CHEMICAL ANALYSIS

С P S Si Mn Νi $\operatorname{\mathtt{Cr}}$ Mo Sn AlNb CE .06 .85 .011 .039 .21 .27 .09 .11 .036 .006 .003 .26 .002 .019

PHYSICAL PROPERTIES

Yield Strength		Tensile Strength		Specimen Area		<u>Elongation</u>			Bend Test	ROA
KSI	MPa	KSI	MPa	Sq In	Sq cm	ક	Gage Ler	ngth	Dia. Result	8
50.8	350.3	68.1	469.5	0.988	6.37	22.8	8 In	200 mm		
52.6	362.7	69.0	475.7	1.011	6.52	23.5	8 In	200 mm		

TENSILE TEST RATIOS

YLD/TENS TENS/YLD YLD/TENS TENS/YLD

.75 1.34 .76 1.31

All manufacturing processes of this product, including electric arc MELTING and continuous CASTING, occurred in the U.S.A. CMTR complies with EN 10204 3.1

"I hereby certify that the contents of this report are correct and accurate. All tests and operations performed by this material manufacturer or its sub-contractors, when applicable, are in compliance with the requirements of the material specifications and applicable purchaser designated requirements."

Tom L. Harrington: Quality Assurance Manager

Signed:

Notary Public (if applicable)

Date:

2 of Page:

Bill To: SIDERTUL SA DE CV RFC# SID930918KR0 AVENIDA PRESIDENTE MASARYK MEXICO CITY DF

Ship To: 7 SIDERTUL SA DE CV 402 GRAND CENTRAL BLVD MILO DISTRIBUTION CENTER LAREDO TX

Order Date:06/17/2011 PO No:4500012651 Mill Order No:3899438 Load No:1394670 Manifest No:2092137

CERTIFIED MATERIAL TEST REPORT GERDAU AMERISTEEL

GERDAU AMERISTEEL

Midlothian Mill 300 Ward Road Midlothian, TX 76065 (972)775-8241

SPECIFICATIONS

11570

W 21 X 68# / W530 X 101

78045

LENGTH 40 FT / 12.192 M

CE

.31

PRODUCT WF BEAMS

ASTM A6-09, A992-06a, A572-07

HEAT NO: 22606090

CHEMICAL ANALYSIS C MnР S Si Cu Νi CrMo Şn AlМb .08 .96 .004 .017 .024 .24 .32 .11 .18 .045 .008 .002 .020

US

GRADE

992/572-50

PHYSICAL PROPERTIES

							_			
Yield Strength		Tensile Strength		Specimen Area		Elongation_			Bend Test	<u>ROA</u>
KSI	MPa	KSI	MPa	Sq In	Sq cm	8	Gage Len	igth	Dia. Result	%
54.4	375.1	71.0	489.5	0.981	6.33	24.4	8 In	200 mm		
55.1	379.9	71.8	495.0	1.001	6.46	24.9	8 In	200 mm		

TENSILE TEST RATIOS

YLD/TENS TENS/YLD YLD/TENS TENS/YLD

MX

SIZE

.77 1.3 1.31 .77

All manufacturing processes of this product, including electric arc MELTING and continuous CASTING, occurred in the U.S.A. CMTR complies with EN 10204 3.1

"I hereby certify that the contents of this report are correct and accurate. All tests and operations performed by this material manufacturer or its sub-contractors, when applicable, are in compliance with the requirements of the material specifications and applicable purchaser designated requirements."

Tom L. Harrington: Quality Assurance Manager

Signed:

Notary Public (if applicable)

Date:

Page: 3 of