Bill To: SIDERTUL SA DE CV RFC# SID930918KR0 AVENIDA PRESIDENTE MASARYK DFMEXICO CITY

Ship To: 7 SIDERTUL SA DE CV 402 GRAND CENTRAL BLVD MILO DISTRIBUTION CENTER LAREDO TX

Order Date:06/17/2011 PO No:4500012651 Mill Order No:3899414 Load No:1399415

Manifest No:2094648

G GERDAU AMERISTEEL

CERTIFIED MATERIAL TEST REPORT GERDAU AMERISTEEL Midlothian Mill

300 Ward Road Midlothian, TX 76065 (972)775-8241

SIZE

MX

GRADE 992/572-50

US

LENGTH 40 FT / 12.192 M

PRODUCT WF BEAMS

SPECIFICATIONS

HEAT NO: 22608980

11570

W 16 X 31# / W410 X 46.1

78045

ASTM A6-09, A992-06a, A572-07

CHEMICAL ANALYSIS

C Ρ S Si Cu Νi Cr Мо Sn Αl Nb CE Mn .002 .003 .28 .08 .88 .011 .018 .21 .30 .10 .12 .035 .006 .018

PHYSICAL PROPERTIES

| Yield Strength | | Tensile Strength | | Specimen Area | | <u>Elongation</u> | | | | Bend Test | ROA |
|----------------|-------|------------------|-------|---------------|-------|-------------------|----------|--------|-----|-------------|-----|
| KSI | MPa | KSI | MPa | Sq In | Sq cm | ક | Gage Ler | ıgth | . 1 | Dia. Result | 용 |
| 60.3 | 415.8 | 75.5 | 520.6 | 0.404 | 2.61 | 25.5 | 8 In | 200 mm | | | |
| 59.9 | 413.0 | 74.6 | 514.3 | 0.407 | 2.63 | 26.2 | 8 In | 200 mm | | | |

TENSILE TEST RATIOS

YLD/TENS TENS/YLD YLD/TENS TENS/YLD

. 8 1.25 . 8 1.24

All manufacturing processes of this product, including electric arc MELTING and continuous CASTING, occurred in the U.S.A. CMTR complies with EN 10204 3.1

"I hereby certify that the contents of this report are correct and accurate. All tests and operations performed by this material manufacturer or its sub-contractors, when applicable, are in compliance with the requirements of the material specifications and applicable purchaser designated requirements."

Tom L. Harrington: Quality Assurance Manager Signed:

Signed:

Notary Public (if applicable)

Date:

Page: 3 of 3