Bill To: GERDAU CORSA S A P I DE CV KM 3 CARRETERA MEXICO-CD SAHAGUN S/N

HG

MX

SIZE

Ship To: 2
GERDAU CORSA S A P I DE CV
402 GRAND CENTRAL BLVD
MILO DISTRIBUTION CENTER
LAREDO TX

Order Date:11/28/2011
PO No:4500077195
Mill Order No:3962881
Load No:1416557
Manifest No:2110996

CERTIFIED MATERIAL TEST REPORT - GERDAU AMERISTEEL

GERDAU AMERISTEEL

Midlothian Mill
300 Ward Road
Midlothian, TX 76065
(972)775-8241

SPECIFICATIONS

SAHAGUN

43990

W 14 X 53# / W360 X 79

78045

LENGTH 40 FT / 12.192 M PRODUCT WF BEAMS

ASTM A6-09, A992-06a, A572-07

HEAT NO: 2261837M

C Mn Ρ S Si Cr Sn Νi Мо v Αl Nb CE.07 .91 .014 .033 .21 .34 .08 .14 .031 .009 .002 .003 .019 .28

US

GRADE

992/572-50

PHYSICAL PROPERTIES

CHEMICAL ANALYSIS

| Yield Strength | | Tensile Strength | | Specimen Area | | Elongation_ | | | Bend Test | ROA | |
|----------------|-------|------------------|-------|---------------|-------|-------------|----------|--------|-------------|-----|--|
| KSI | MPa | KSI | MPa | Sq In | Sq cm | % | Gage Ler | ngth | Dia. Result | | |
| 58.3 | 402.0 | 73.3 | 505.4 | 0.923 | 5.95 | 25.2 | 8 In | 200 mm | | | |
| 56.0 | 386.1 | 73.5 | 506.8 | 0.934 | 6.03 | 26.1 | 8 In | 200 mm | | | |

TENSILE TEST RATIOS

YLD/TENS TENS/YLD YLD/TENS TENS/YLD

.8 1.26 .76 1.31

All manufacturing processes of this product, including electric arc MELTING and continuous CASTING, occurred in the U.S.A. CMTR complies with EN 10204 3.1

"I hereby certify that the contents of this report are correct and accurate. All tests and operations performed by this material manufacturer or its sub-contractors, when applicable, are in compliance with the requirements of the material specifications and applicable purchaser designated requirements."

Signed:
Tom L. Harrington: Quality Assurance Manager

Date: Jan. 04, 2012 Signed:
Notary Public

Notary Public (if applicable)

Page: 2 of

Date: