Bill To: GERDAU CORSA S A P I DE CV KM 3 CARRETERA MEXICO-

GERDAU CORSA S A P I DE CV 402 GRAND CENTRAL BLVD MILO DISTRIBUTION CENTER LAREDO TX

Order Date:02/10/2012 PO No:4500115755 Mill Order No:4002381 Load No:1431424

Manifest No:2124278

CERTIFIED MATERIAL TEST REPORT GERDAU AMERISTEEL

GO GERDAU AMERISTEEL

Midlothian Mill 300 Ward Road Midlothian, TX 76065 (972)775-8241

SIZE

HG

MΧ

LENGTH 40 FT / 12.192 M

PRODUCT WF BEAMS

SPECIFICATIONS

HEAT NO: 22636580

CD SAHAGUN S/N

SAHAGUN

43990

W 24 X 68# / W610 X 101

Ship To: 1

78045

992/572-50

ASTM A6-09, A992-06a, A572-07

CHEMICAL ANALYSIS

C Ρ S Si Νi Cr snAl Mn Cu Mo NbCE .07 .009 .038 .21 .08 .08 .029 .008 .001 .003 .015 .25 .80 .26

US

GRADE

PHYSICAL PROPERTIES

| Yield Strength | | Tensile Strength | | Specimen Area | | <u>Elongation</u> | | | Bend Test | ROA |
|----------------|-------|------------------|-------|---------------|-------|-------------------|-------------|--------|-------------|-----|
| KSI | MPa | KSI | MPa | Sq In | Sq cm | % | Gage Length | | Dia. Result | 용 |
| 53.7 | 370.2 | 69.4 | 478.5 | 0.843 | 5.44 | 26.4 | 8 In | 200 mm | | |
| 52.9 | 364.7 | 70.5 | 486.1 | 0.840 | 5.42 | 28.3 | 8 In | 200 mm | | |

TENSILE TEST RATIOS

YLD/TENS TENS/YLD YLD/TENS TENS/YLD

.77 1.29 .75 1.33

All manufacturing processes of this product, including electric arc MELTING and continuous CASTING, occurred in the U.S.A. CMTR complies with EN 10204 3.1

"I hereby certify that the contents of this report are correct and accurate. All tests and operations performed by this material manufacturer or its sub-contractors, when applicable, are in compliance with the requirements of the material specifications and applicable purchaser designated requirements."

Tom L. Harrington: Quality Assurance Manager

Signed: Notary Public (if applicable) Date:

Page:

1 of