Bill To: SIDERTUL SA DE CV RFC# SID930918KR0 AVENIDA PRESIDENTE MASARYK MEXICO CITY DF 11570 ΜX SPECIFICATIONS

Ship To: 1 SIDERTUL SA DE CV 402 GRAND CENTRAL BLVD MILO DISTRIBUTION CENTER LAREDO TX 78045 US

Order Date: 02/18/2011 PO No:4500000574 Mill Order No:3860076 Load No:1385580 Manifest No:2081612

CERTIFIED MATERIAL TEST REPORT GERDAU AMERISTEEL Midlothian Mill

G GERDAU AMERISTEEL

300 Ward Road Midlothian, TX 76065 (972)775-8241

SIZE

W 24 X 62# / W610 X 92

LENGTH 40 FT / 12.192 M

PRODUCT WF BEAMS

ASTM A6-09, A992-06a, A572-07

HEAT NO: 22596750

CHEMICAL ANALYSIS С Mn S Si Cu Νi Cr Мо Sn Al Nb CE .08 .87 .016 .037 .30 .41 .11 .10 .033 .013 .002 .003 .29 .023

PHYSICAL PROPERTIES

Yield Strength		Tensile Strength		Specimen Area		Elongation			Bend Test	ROA
KSI	MPa	KSI	MPa	Sq In	Sq cm	8	Gage Ler	ngth	Dia. Result	
56.5	389.6	73.6	507.5	0.854	5.51	23.7	8 In	200 mm		
56.5	389.6	74.0	510.2	0.875	5.65	23.3	8 In	200 mm		

GRADE

992/572-50

TENSILE TEST RATIOS

YLD/TENS YLD/TENS

.76 .77

All manufacturing processes of this product, including electric arc MELTING and continuous CASTING, occurred in the U.S.A. CMTR complies with EN 10204 3.1

"I hereby certify that the contents of this report are correct and accurate. All tests and operations performed by this material manufacturer or its sub-contractors, when applicable, are in compliance with the requirements of the material specifications and applicable purchaser designated requirements."

Tom L. Harrington: Quality Assurance Manager

Signed:

Notary Public (if applicable)

Date:

Page: 4 of Bill To: SIDERTUL SA DE CV RFC# SID930918KR0 AVENIDA PRESIDENTE MASARYK MEXICO CITY DF ΜX

Ship To: 1 SIDERTUL SA DE CV 402 GRAND CENTRAL BLVD MILO DISTRIBUTION CENTER LAREDO TX US 78045

Order Date: 02/18/2011 PO No:4500000574 Mill Order No:3860076 Load No:1385580 Manifest No:2081612

CERTIFIED MATERIAL TEST REPORT GERDAU AMERISTEEL

GERDAU AMERISTEEL

Midlothian Mill 300 Ward Road Midlothian, TX 76065 (972)775-8241

SPECIFICATIONS

SIZE W 24 X 62# / W610 X 92

LENGTH 40 FT / 12.192 M

PRODUCT WF BEAMS

ASTM A6-09, A992-06a, A572-07

HEAT NO: 2258745M

11570

C Mn Ρ S Si Νi Mo AlCu Cr Sn Nb CE .08 .92 .018 .029 .23 .33 .09 .029 .002 .13 .016 .003 .020 .29

PHYSICAL PROPERTIES

CHEMICAL ANALYSIS

Yield Strength		Tensile Strength		Specimen Area		Elongation			Bend Test	
KSI	MPa	KSI	MPa	Sq In	Sq cm	g g	Gage Length		Dia. Result	8
56.5	389.6	71.8	495.0	0.863	5.57	24.5	8 In	200 mm		
56.1	386.8	71.8	495.0	0.859	5.54	23.8	8 In	200 mm		

GRADE

992/572-50

TENSILE TEST RATIOS YLD/TENS YLD/TENS .78 .79

All manufacturing processes of this product, including electric arc MELTING and continuous CASTING, occurred in the U.S.A. CMTR complies with EN 10204 3.1

"I hereby certify that the contents of this report are correct and accurate. All tests and operations performed by this material manufacturer or its sub-contractors, when applicable, are in compliance with the requirements of the material specifications and applicable purchaser designated requirements."

Date: Jul. 08, 2011
Tom L. Harrington: Quality Assurance Manager

Signed: Notary Public (if applicable) Date:

Page:

5 of

5