Bill To: SIDERTUL SA DE CV RFC# SID930918KR0 AVENIDA PRESIDENTE MASARYK MEXICO CITY DF 11570 ΜX

Ship To: 1 SIDERTUL SA DE CV 402 GRAND CENTRAL BLVD MILO DISTRIBUTION CENTER LAREDO TX 78045 US

Order Date:02/18/2011 PO No:4500000574 Mill Order No:3860076 Load No:1385580 Manifest No:2081612

CERTIFIED MATERIAL TEST REPORT GERDAU AMERISTEEL Midlothian Mill

GERDAU AMERISTEEL

300 Ward Road Midlothian, TX 76065 (972)775-8241

SPECIFICATIONS

W 24 X 62# / W610 X 92

SIZE

LENGTH 40 FT / 12.192 M PRODUCT WF BEAMS

ASTM A6-09, A992-06a, A572-07

HEAT NO: 22596750

C Mn Ρ Si Cu Νi CrMo Sn Al Nb CE .08 .87 .016 .037 .30 .41 .11 .10 .033 .013 .002 .003 .023 .29

PHYSICAL PROPERTIES

CHEMICAL ANALYSIS

Yield Strength		Tensile Strength		Specimen Area		Elongation			Bend Test	ROA
KSI	MPa	KSI	MPa	Sq In	Sq cm	8	Gage Lei	ngth	Dia. Result	8
56.5	389.6	73.6	507.5	0.854	5.51	23.7	8 In	200 mm		
56.5	389.6	74.0	510.2	0.875	5.65	23.3	8 In	200 mm		

GRADE

992/572-50

TENSILE TEST RATIOS YLD/TENS YLD/TENS

.77

CMTR complies with EN 10204 3.1

.76

All manufacturing processes of this product, including electric arc MELTING and continuous CASTING, occurred in the U.S.A.

"I hereby certify that the contents of this report are correct and accurate. All tests and operations performed by this material manufacturer or its sub-contractors, when applicable, are in compliance with the requirements of the material specifications and applicable purchaser designated requirements."

Tom L. Harrington: Quality Assurance Manager Signed: Date: Notary Public (if applicable)

Page: 4 of Bill To: SIDERTUL SA DE CV RFC# SID930918KR0 AVENIDA PRESIDENTE MASARYK MEXICO CITY DF MΧ 11570

Ship To: 1 SIDERTUL SA DE CV 402 GRAND CENTRAL BLVD MILO DISTRIBUTION CENTER LAREDO TX 78045 US

Order Date:02/18/2011 PO No:4500000574 Mill Order No:3860078 Load No:1385528 Manifest No:2081625

CERTIFIED MATERIAL TEST REPORT GERDAU AMERISTEEL Midlothian Mill

GERDAU AMERISTEEL

CE

.3

300 Ward Road Midlothian, TX 76065 (972)775-8241

W 24 X 76# / W610 X 113

SIZE

LENGTH 40 FT / 12.192 M

PRODUCT WF BEAMS

SPECIFICATIONS

ASTM A6-09, A992-06a, A572-07

HEAT NO: 22596230

CHEMICAL ANALYSIS C Mn Ρ Si Cu Ni CrMo Sn AlNb .026 .07 .95 .036 .29 .42 .09 .18 .029 .010 .002 .003 .022

PHYSICAL PROPERTIES

Yield Strength		Tensile Strength		Specimen Area		Elongation			Bend Test	
KSI	KSI MPa	KSI	MPa	Sq In	Sq cm	90	Gage Le	ngth	Dia. Result	ROA %
58.4	402.7	76.4	526.8	0.984	6.35	24.8	8 In	200 mm		
58.4	402.7	76.1	524.7	0.971	6.26	25.3	8 In	200 mm		

GRADE

992/572-50

TENSILE TEST RATIOS YLD/TENS YLD/TENS .76 .77

All manufacturing processes of this product, including electric arc MELTING and continuous CASTING, occurred in the U.S.A. CMTR complies with EN 10204 3.1

"I hereby certify that the contents of this report are correct and accurate. All tests and operations performed by this material manufacturer or its sub-contractors, when applicable, are in compliance with the requirements of the material specifications and applicable purchaser designated requirements."

Tom L. Harrington: Quality Assurance Manager

Signed:

Notary Public (if applicable)

Date:

Page: 1 of