Bill To: SIDERTUL SA DE CV RFC# SID930918KR0 AVENIDA PRESIDENTE MASARYK MEXICO CITY DF ΜX 11570

Ship To: 1 SIDERTUL SA DE CV 402 GRAND CENTRAL BLVD MILO DISTRIBUTION CENTER TX LAREDO 78045 US

Order Date:08/04/2010 PO No:A-00018396-GC Mill Order No:3764263 Load No:1327577

Manifest No:2028015

GERDAU AMERISTEEL

Midlothian Mill 300 Ward Road Midlothian, TX 76065 (972)775-8241

ROA

GERDAU AMERISTEEL

W 14 X 34# / W360 X 51

GRADE 992/572-50

LENGTH 40 FT / 12.192 M

PRODUCT WF BEAMS

CERTIFIED MATERIAL TEST REPORT

SPECIFICATIONS

HEAT NO: 22550630

ASTM A6-09, A992-06a, A572-07

CHEMICAL ANALYSIS

V Cu Νi Cr Мо Sn Al Nb CE С Mn Ρ S Si .31 .10 .89 .007 .026 .27 .34 .10 .11 .031 .011 .002 .003 .017

PHYSICAL PROPERTIES

Yield Strength		Tensile Strength		Specimen Area		Elongation			Bend Test
KSI	MPa	KSI	MPa	Sq In	Sq cm	ક	Gage Length		Dia. Result
57.5	396.4	77.8	536.4	0.620	4.00	23.9	8 In	200 mm	
56.1	386.8	76.2	525.4	0.641	4.14	25.0	8 In	200 mm	

TENSILE TEST RATIOS

YLD/TENS

.74

All manufacturing processes of this product, including electric arc MELTING and continuous CASTING, occurred in the U.S.A. CMTR complies with EN 10204 3.1

"I hereby certify that the contents of this report are correct and accurate. All tests and operations performed by this material manufacturer or its sub-contractors, when applicable, are in compliance with the requirements of the material specifications and applicable purchaser designated requirements."

Signed: Date: Sep. 14, 2010
Tom L. Harrington: Quality Assurance Manager Date: Notary Public (if applicable) Page: 1 of Bill To:
SIDERTUL SA DE CV
RFC# SID930918KR0
AVENIDA PRESIDENTE MASARYK
MEXICO CITY DF
11570 MX

Ship To: 1
SIDERTUL SA DE CV
402 GRAND CENTRAL BLVD
MILO DISTRIBUTION CENTER
LAREDO TX
78045 US

Order Date:08/04/2010 PO No:A-00018396-GC Mill Order No:3764263 Load No:1327577 Manifest No:2028015

CERTIFIED MATERIAL TEST REPORT

GERDAU AMERISTEEL

Midlothian Mill

GERDAU AMERISTEEL

300 Ward Road Midlothian, TX 76065 (972)775-8241

ROA

SIZE

W 14 X 34# / W360 X 51

GRADE 992/572-50 LENGTH 40 FT / 12.192 M PRODUCT WF BEAMS

DDUCT

SPECIFICATIONS

HEAT NO: 22559230

ASTM A6-09, A992-06a, A572-07

CHEMICAL ANALYSIS

Р S Si Cu Νi Cr Mo Sn Al Nb CE С Mn .003 .019 .29 .08 . 92 .009 .031 .23 .34 .13 .10 .035 .011 .002

PHYSICAL PROPERTIES

Yield Strength		Tensile Strength		Specimen Area		Elongation			Bend Test
KSI	MPa	KSI	MPa	Sq In	Sq cm	% Gage Length		ngth	Dia. Result
56.0	386.1	74.1	510.9	0.632	4.08	23.8	8 In	200 mm	
55.4	382 D	73.3	505.4	0.626	4 04	23.7	8 Tn	200 mm	

TENSILE TEST RATIOS

YLD/TENS

.76

All manufacturing processes of this product, including electric arc MELTING and continuous CASTING, occurred in the U.S.A. CMTR complies with EN 10204 3.1

"I hereby certify that the contents of this report are correct and accurate. All tests and operations performed by this material manufacturer or its sub-contractors, when applicable, are in compliance with the requirements of the material specifications and applicable purchaser designated requirements."

Signed: \_\_\_\_\_\_Date: Sep. 14, 2010 Signed: \_\_\_\_\_\_ Notary Public (if applicable) Date: \_\_\_\_\_\_ Page: 2 of 2