Bill To: Ship To: 1 CERTIFIED MATERIAL TEST REPORT Order Date:11/15/2011 GERDAU CORSA S A P I DE CV GERDAU CORSA S A P I DE CV PO No:4500075345 GERDAU AMERISTEEL KM 3 CARRETERA MEXICO-402 GRAND CENTRAL BLVD Mill Order No:3957813 Midlothian Mill GERDAU AMERISTEEL CD SAHAGUN S/N MILO DISTRIBUTION CENTER Load No:1417536 300 Ward Road SAHAGUN HG LAREDO TX Manifest No:2112133 Midlothian, TX 76065 ΜX 43990 78045 US (972)775-8241 STZE GRADE LENGTH PRODUCT W 10 X 39# / W250 X 58 992/572-50 40 FT / 12.192 M WF BEAMS SPECIFICATIONS ASTM A6-09, A992-06a, A572-07 HEAT NO: 22625300 CHEMICAL ANALYSIS C Mn Ρ S Si $\operatorname{\mathtt{Cr}}$ Мо Sn v Al Nb CE .07 .87 .027 .022 .24 .40 .10 .16 .038 .010 .002 .004 .015 .29 PHYSICAL PROPERTIES Yield Strength Tensile Strength Specimen Area Elongation Bend Test ROA KST MPa KSI Sq In MPa Sq cm Gage Length Dia. Result 앟 54.4 375.1 72.9 502.6 0.728 4.70 25.1 8 In 200 mm 54.5 73.5 375.8 506.8 0.752 4.85 24.9 8 In 200 mm

TENSILE TEST RATIOS

YLD/TENS TENS/YLD YLD/TENS TENS/YLD

.75 1.34 .74 1.35

All manufacturing processes of this product, including electric arc MELTING and continuous CASTING, occurred in the U.S.A. CMTR complies with EN 10204 3.1

"I hereby certify that the contents of this report are correct and accurate. All tests and operations performed by this material manufacturer or its sub-contractors, when applicable, are in compliance with the requirements of the material specifications and applicable purchaser designated requirements."

Date: Jan. 10, 2012 Signed: Date: Tom L. Harrington: Quality Assurance Manager Notary Public (if applicable) 2 of Page: