CERTIFIED MATERIAL TEST REPORT Bill To: Ship To: 1 Order Date:11/29/2011 GERDAU CORSA S A P I DE CV GERDAU CORSA S A P I DE CV PO No:4500085476 GERDAU AMERISTEEL KM 3 CARRETERA MEXICO-402 GRAND CENTRAL BLVD Mill Order No:3963328 Midlothian Mill GERDAU AMERISTEEL CD SAHAGUN S/N MILO DISTRIBUTION CENTER Load No:1414296 300 Ward Road SAHAGUN HG LAREDO Manifest No:2108680 TX Midlothian, TX 76065 43990 MX 78045 US (972)775-8241 SIZE GRADE LENGTH PRODUCT W 18 X 60# / W460 X 89 992/572-50 40 FT / 12.192 M WF BEAMS SPECIFICATIONS ASTM A6-09, A992-06a, A572-07 HEAT NO: 22621330 CHEMICAL ANALYSIS C Mn Ρ S Si Cu Νi CrМо v Al Sn Nb CE .06 .88 .010 .035 .25 .43 .12 .12 .040 .011 .002 .003 .023 PHYSICAL PROPERTIES Yield Strength Tensile Strength Specimen Area Elongation Bend Test ROA KSI MPa KSI MPa Sq In Sq cm Gage Length Dia. Result 54.3 374.4 70.4 485.4 0.982 6.34 24.9 8 In 200 mm 54.6 376.5 71.2 490.9 0.980 6.32 23.8 8 Tn 200 mm TENSILE TEST RATIOS YLD/TENS TENS/YLD YLD/TENS TENS/YLD .77 1.3 .77 1.3

All manufacturing processes of this product, including electric arc MELTING and continuous CASTING, occurred in the U.S.A. CMTR complies with EN 10204 3.1

"I hereby certify that the contents of this report are correct and accurate. All tests and operations performed by this material manufacturer or its sub-contractors, when applicable, are in compliance with the requirements of the material specifications and applicable purchaser designated requirements."

Page: 1 of 1