

**NUCOR**  
**NUCOR CORPORATION**  
**NUCOR STEEL TEXAS**

**Mill Certification**  
**8/11/2014**

MTR #: 0000043915  
 8812 Hwy 79 W  
 Jewett, TX 75846  
 (903) 626-4461  
 Fax: (903) 626-6290

Sold To: PLESA ANAHUAC Y CIAS SA DE CV  
 AV VALLE DE LAS ALAMEDAS  
 NO 66 0  
 TULTITLANMEX 54940  
 MEXICO  
 551-08-38-570  
 Fax: 555-31-01-918

Ship To: PLESA TULTITLAN (LECHERIA)  
 AV VALLE DE LAS ALAMEDAS NO.  
 66 -O COL. SAN FRANCISCO CHILP  
 SPUR: 12-831-94 AND 12-832-94  
 LECHERIA MEX 54940  
 MEXICO  
 956-54-72-800

Customer P.O.	18878	Sales Order	206047.13
Product Group	Merchant Bar Quality	Part Number	2508011548010W0
Grade	NUCOR MULTIGRADE	Lot #	JW1410633451
Size	8x11.5# Channel	Heat #	JW14106334
Product	8x11.5# Channel 40' NUCOR MULTIGRADE	B.L. Number	J1-679669
Description	NUCOR MULTIGRADE	Load Number	J1-283455
Customer Spec		Customer Part #	

I hereby certify that the material described herein has been manufactured in accordance with the specifications and standards listed above and that it satisfies those requirements.

Roll Date: 7/30/2014 Melt Date: 7/27/2014 Qty Shipped LBS: 82,800 Qty Shipped Pcs: 180

C	Mn	P	S	Si	Cu	Ni	Cr	Mo	V	Cb	Sn
0.13%	0.86%	0.011%	0.032%	0.19%	0.34%	0.20%	0.14%	0.060%	0.0497%	0.001%	0.013%
CE4020	CEA529										
0.36%	0.39%										

CE4020: C. E. CSA G4020, AASHTO M270  
 CEA529: A529 CARBON EQUIVALENT

Yield 1: 58,600psi (404MPa) Tensile 1: 75,200psi (518MPa) Elongation: 22% in 8"(% in 203.3mm)  
 Yield 2: 59,300psi (409MPa) Tensile 2: 75,600psi (521MPa) Elongation 22% in 8"(% in 203.3mm)

Specification Comments: NUCOR MULTIGRADE MEETS THE REQUIREMENTS OF: ASTM A36/A36M-08, A529/529M-05(2009)  
 GR50(345), A572/572M-07 GR50(345), A709/709M-10 GR36(250) & GR50(345), CSA G40.21-04 GR44W(300W) & GR50W(350W)  
 AASHTO M270/M270M-10 GR36(270) & GR50(345), ASME SA36/SA36M-07

Comments: E-mail: websales@nstexas.com

1. All manufacturing processes of the steel, including melting, have been performed in the U.S.A.
2. Mercury in any form has not been used in the production or testing of this product.
3. Welding or weld repair was not performed on this material.
4. This material conforms to the specifications described on this document and may not be reproduced, except in full, without written approval of Nucor Corporation.
5. Results reported for ASTM E45 (Inclusion content) and ASTM E381 (Macro-etch) are provided as interpretation of ASTM procedures.

*Bhargava R Vantari*

Bhargava R Vantari  
 Division Metallurgist