

Mill Certification 10/3/2014

MTR #: 0000056276 8812 Hwy 79 W Jewett, TX 75846 (903) 626-4461 Fax: (903) 626-6290

PLESA ANAHUAC Y CIAS SA DE CV AV VALLE DE LAB ALAMEDAS NO 66 0 TULTITLANMEX 54940 MEXICO 551-08-38-570 Fax: 555-31-01-918

Ship To: PLESA TULTITLAN (LECHERIA)
AV VALLE DE LAS ALAMEDAS NO.
66 -O COL. SAN FRANCISCO CHILP
SPUR: 12-831-94 AND 12-832-94
LECHERIAMEX 54940
MEXICO
056 54 72 900

956-54-72-800

Customer P.O.	19251	Sales Order	207939.7
Product Group	Merchant Bar Quality	Part Number	2030037548010W0
Grade	NUCOR MULTIGRADE	Lot#	JW1410753051
Size	3x3x3/8 Angle	Heat #	JW14107530
Product	3x3x3/8 Angle 40' NUCOR MULTIGRADE	B.L. Number	J1-685537
Description	NUCOR MULTIGRADE	. Load Number	J1-287434
Customer Spec	•	Customer Part #	

I hereby certify that the material described herein has been manufactured in accordance with the specifications and standards listed above and that it satisfies those requirements

Roll Date: 9/4/2014 Melt Date: 9/1/2014 Qty Shipped LBS: 20,160 Qty Shipped Pcs: 70

Р С s· Si Cu Cr V٠ Cb Sn Mn Ni Mo 0.13% 0.89% 0.013% 0.029% 0.21% 0.39% 0.18% 0.17% 0.050% 0.0423% 0.002% 0.018%

CE4020 CEA529 . 0.37% 0.40%

CE4020; C. E. CSA-G4020, AASHTO M270 CEA529; A529 CARBON EQUIVALENT

Yield 1:57,100psi (394MPa)

Tensile 1: 75,100psi (518MPa)

Elongation: 22% in 8"(% in 203.3mm)

Yield 2: 58,000psi (400MPa)

Tensile 2: 75,400psi (520MPa)

Elongation 20% in 8"(% in 203.3mm)

Specification Comments: NUCOR MULTIGRADE MEETS THE REQUIREMENTS OF: ASTM A36/A36M-08, A529/529M-05(2009) GR50(345), A572/572M-07 GR50(345), A709/709M-10 GR36(250) & GR50(345), CSA G40.21-04 GR44W(300W) & GR50W(350W) AASHTO M270/M270M-10 GR36(270) & GR50(345), ASME SA36/SA36M-07

Comments: E-mail: websales@nstexas.com

- 1. All manufacturing processes of the steel, including melting, have been performed in the U.S.A.
 2. Mercury in any form has not been used in the production or testing of this product.
 3. Welding or weld repair was not performed on this material.
 4. This material conforms to the specifications described on this document and may not be reproduced, except in full, without written approval of Nucor Corporation.
 5. Results reported for ASTM E45 (Inclusion content) and ASTM E381 (Macro-etch) are provided as interpretation of ASTM procedures.

Rola R Vantari