SOLD TO:

SHIP

TO:

NUCOR NUCOR CORPORATION **NUCOR STEEL TEXAS** 

**CERTIFIED MILL TEST REPORT** 

Page: 1

Ship from:

Nucor Steel - Texas 8812 Hwy 79 W JEWETT, TX 75846

B.L. Number:

Date: 7-Mar-2012

800-527-6445

Load Number:

Material Safety Data Sheets are available at www.nucorbar.com or by contacting your inside sales representative.

NBMG-08 January 1, 2012

LOT#	DESCRIPTION	PHYSICAL TESTS					CHEMICAL TESTS						
HEAT#		YIELD P.S.I.	TENSILE P.S.I.	ELONG % IN 8"	BEND	WT% DEF	C Ni Mn	Cr P	Mo	S V S	Cb Cb	Cu Sn	C.E.
JW1210031801 JW12100318	Nucor Steel - Texas 4x5.4# Channel 20' A36/A529GR50 ASTM A36-08, A529-05, A709-09a G	60,900	78,800 543MPa 78,600 542MPa	23.0% 22.0%			.11 .12 GE4020 0.31	.86 .09 CEA52	.006 .029 9	.037 .001	.21 .011	.36	
JW1210031801 JW12100318	R36, ASME SA36-07 Ed 11 Ad MEETS ASTM A572-50 TYPE 1 Nucor Steel - Texas 4x5.4# Channel	61,400 423MPa	78,800 543MPa	23.0%			.11 .12	.86 .09	.006 .029	.037 .001	.21 .011	.36	
	40' A36/A529GR50 ASTM A36-08, A529-05, A709-09a G R36, ASME SA36-07 Ed 11 Ad MEETS ASTM A572-50 TYPE 1	60,900 420MPa	78,600 542MPa	22.0%			CE4020 0.31	CEA529 0.35	9				
	Will make A572 GR 50												

I hereby certify that the material described herein has been manufactured in accordance with the specifications and standards listed above and that it satisfies those requirements.

1.) Weld repair was not performed on this material.

2.) Melted and Manufactured in the United States.

3.) Mercury, Radium, or Alpha source materials in any form have not been used in the production of this material.

QUALITY ASSURANCE:

Nathan Stewart

