DATE	1/26/12
INVOICE NO.	459450
BILL OF LADING	53224
CUSTOMER NO.	5446
CUSTOMER P.O.	600296

NUCOR-YAMATO STEEL CO.

P.O. BOX 1228 ● BLYTHEVILLE,AR 72316

CERTIFIED MILL TEST REPORT

100% MELTED AND MANUFACTURED IN U.S.A.
All shapes produced by Nucor-Yamato Steel are cast and rolled to a fully killed and fine grain practice.

SHIP TO
FB C/O JORGE MIGUEL MEDRANO SANCHEZ
HIDALGO 3530 PAT 4100
FINAL: SAN LUIS POTOSI SLP MX
NUEVO LAREDO, TM 88000

SPECIFICATIONS
ASTM A992/A992M-06a A572/A572M GR50-07
ASTM A709/A709M-09 GR50 (345)
ASTM A709/A709M-09 GR50S (345S)
ASTM A6/A6M-09

46231

SOLD TO
FERRE BARNIEDO, SA DE CV
AV REVOLUCION #81 COL SAN CRISTOBAL
ECATEPEC DE MORELOS
EDO, MEXICO CP 55000

ITEM #	ITEM DESCRIPTION	QTY	HEAT #	MECHANICAL PROPERTIES: YIELD TO TENSILE RATIO	YIELD STRENGTH PSI / MPa	TENSILE STRENGTH PSI / MPa	ELONG % / %	CHARPY IMPACT TEMP °F / °C	IMPACT ENERGY FT-LBS / JOULES	CHEMICAL PROPERTIES: C	Mn	P	S	Si	Cu	Ni	Cr	Mo / Sn	V / Pcm	Cb	CE / CI
	30 -116.0	8	379418	.78	56000	72000	28			.07	1.01	.014	.026	.25	.29	.13	.13	.04	.00	.019	.30
	40'			.76	55000	72000	29											.01	.16		
	W760 x173.0				386	496	28														
	12.192 M				379	496	29														
2	W30 -116.0	15	379420	.78	56000	72000	27			.07	1.00	.017	.027	.25	.34	.13	.15	.03	.00	.019	.31
	40'			.78	56000	72000	28											.01	.16		
	W760 x173.0				386	496	27														
	12.192 M				386	496	28														
3	W30 -116.0	13	379422	.78	57000	73000	28			.07	1.02	.013	.028	.26	.30	.12	.13	.04	.00	.019	.30
	40'			.77	58000	75000	26											.01	.16		
	W760 x173.0				393	503	28														
	12.192 M				400	517	26														

FERRE BARNIEDO, S.A. DE C.V.
ESTE CERTIFICADO ES COPIA FIEL
DEL ORIGINAL DE NUESTROS ARCHIVOS
AMPARA LA REMISION No.
58-36-10-00
ventas@ferrebarniedo.com.mx

Pcm = C + Si/30 + Mn/20 + Cu/20 + Ni/60 + Cr/20 + Mn/15 + V/10 + 5 B B=Approx. .0005

CARBON EQUIVALENT: CE = CE(IIW) = C + Mn/6 + (Cr+Mo+V)/5 + (Ni +Cu)/15

Mercury has not been used in the direct manufacturing of this material.

Corrosion Index: CI=26.01(%Cu)+3.88(%Ni)+1.20(%Cr)+1.49(%Si)+17.28(%P)-7.29(%Cu)(%Ni)-9.10(%Ni)(%P)-33.39(%Cu)^2

ELONGATION BASED ON 8.00 INCH GAUGE LENGTH

I hereby certify that the contents of this report are accurate and correct. All test results and operations performed by this material manufacturer are in compliance with the requirements of the material specifications listed in the Specifications Block above.

Gary Lemmell

QUALITY ASSURANCE

CUSTOMER COPY

STATE OF ARKANSAS COUNTY OF MISSISSIPPI
SWORN TO AND SUBSCRIBED BEFORE ME THIS
26 Day of 01/12

Charlene Wallis NOTARY PUBLIC

MY COMMISSION EXPIRES 10/21/2013

CHARLENE WALLIS MY Comm. Exp. NOTARY PUBLIC 10-21-2013 MISSISSIPPI CO. ARKANSAS