

Arcelor Thüringen GmbH
Postfach 1163
07331 Unterwellenborn
Germany

A08 Order Nr: 1700005933

A07 Customer Nr: 2456

B02 Quality: A36/A572 DUAL
according to: ASTM A36/ASTM A572 GR50
DUAL CERTIFICATION

A02 Inspection Certificate 3.1

ASTM A6

A05
A06
Arcelor International America, LLC
Mill business, Long Products
350 Hudson Street
10014 NEW YORK
UNITED STATES OF AMERICA


Lot Nr	Heat Nr	Dimension	Length	Pieces	Weight [t]	Customer Nr
003	46823	W 16X5,5X26	40'	6	2,830	

Heat Analysis [%]

Heat Nr	C	Si	Mn	P	S	N	Nb	V
max	0.20	0.40		0.040	0.050		0.050	
min							0.005	
46823	0.07	0.20	1.16	0.020	0.029	0.004	0.012	0.007

Heat Nr	Tensile test Yield stress [PSI]	Tensile strength [PSI]	Elongation 50 mm [%]	Ys/Ts
max		80000		
min	50000	65000	21,0	
46823	54230	72210	42,9	0,75

Z03 Works inspector
Renate Schmidt



Z02 Apr 10, 2007