CERTIFIED MATERIAL TEST REPORT Bill To: Ship To: 5 Order Date:05/20/2010 SIDERTUL SA DE CV SIDERTUL SA DE CV GERDAU AMERISTEEL PO No:PLESA-TUTL Midlothian Mill RFC# SID930918KR0 402 GRAND CENTRAL BLVD Mill Order No:3737564 AVENIDA PRESIDENTE MASARYK MILO DISTRIBUTION CENTER Load No:1313250 300 Ward Road GERDAU AMERISTEEL MEXICO CITY DF LAREDO TXManifest No:2012462 Midlothian, TX 76065 11570 MX 78045 US (972)775-8241 STZE GRADE LENGTH PRODUCT W 16 X 45# / W410 X 67 992/572-50 40 FT / 12.192 M WF BEAMS SPECIFICATIONS ASTM A6-05a, A992-06a, A572-06 HEAT NO: 22548300 CHEMICAL ANALYSIS C P Mn S Si Cu Ni CrMo Sn Al Nb CE .08 .91 .008 .036 .22 .33 .08 .09 .010 .026 .001 .003 .017 .28

PHYSICAL PROPERTIES

Yield Strength		Tensile Strength		Specimen Area		Elongation			Bend Test	ROA
KSI	MPa	KSI	MPa	Sq In	Sq cm	8	Gage Length		Dia. Result	- <del></del>
55.0	379.2	72.2	497.8	0.774	4.99	22.6	8 In	200 mm		
55.4	382.0	72.6	500.6	0.784	5.06	24.1	8 In	200 mm		

TENSILE TEST RATIOS

YLD/TENS

.76

All manufacturing processes of this product, including electric arc MELTING and continuous CASTING, occurred in the U.S.A. CMTR complies with EN 10204 3.1

"I hereby certify that the contents of this report are correct and accurate. All tests and operations performed by this material manufacturer or its sub-contractors, when applicable, are in compliance with the requirements of the material specifications and applicable purchaser designated requirements."

Page: 2 of 2