CERTIFIED MATERIAL TEST REPORT

Tube Forgings of America, Inc. 5200 NW Front Avenue Portland, OR 97210

ISO 9001-2000 Certified 8/18/2005

Sold To: PLESA ANÁHUAC y CÍAS, S.A. de C.V.

AV. VALLE DE LAS ALAMEDAS NO. 66-A TULTITLAN, EDO., MEX. C. P.54940

Customer PO Reference:

133086 38350 103

Attention To:

TFA Sales Order:

Customer ID:

Ship To: SPECIALISTS IN TRANSIT FORWARDING

1801 MARKLEY MODERN INDUSTRIAL PA

LAREDO, TX 78041

Test Bar Type:

ROUND

Grade: WPB TFA Part ID: 20018

Yield (PSI): Tensile (PSI): 41200 70500 31.50

Description: **Ouantity:**

TFA Heat Code:

20 STD CAP OSM

P477

% Elong In 4D B.H.N.: 106

Mill: Mill Heat:

Process:

V02001 WPB-CSS Tensile Orientation:

LONGITUDINAL

Customer Part ID:

С	MN	Р	S	SI	MO	CR	NI	CU	V	СВ	В	TI	AL	C.E.	
0.200	0.920	0.018	0.006	0.260	0.020	0.020	0.020	0.020	0.002	0.003				0.36	

Coupon Size:	Ft. Lbs	% Shear	Lateral Expansion (Mils)
Charpy V notch test at degrees F:	1:	1:	1:
Charpy Orientation:	2:	2:	2:
Charpy Orientation.	3:	3:	3:
	Avg:	Avg:	

1. THIS MATERIAL WAS COLD FORMED AND STRESS RELIEVED AT 1200F AND AIR COOLED AFTER THE COLD FORMING, 2, THE STARTING MATERIAL IS PLATE WHICH MEETS THE CHEMICAL AND PHYSICAL REQUIREMENTS OF ASTM A234 GR WPB. 3. THE HARDNESS DOES NOT EXCEED 197 BHN PART TO PART. 4. THIS PRODUCT IS SEAMLESS.

THE MATERIAL IS MANUFACTURED TO ASTM A 234 GR WPB REV: 03. ALSO PER ASME SEC II SA 234 GR WPB,2001 EDITION THRU ALL ADDENDAS AT TIME OF ORDER. 2. DESIGN AND DIMENSIONS TO ASME B16,9-2003 OR MSS-SP-75-98 AS APPLICABLE BY DESIGN. 3.PER NACE MR-01-75, 2003 REVISION. OUR QUALITY SYSTEM HAS BEEN REGISTERED BY (ABS) TO (ISO-9001. REV: 2000), CERTIFICATE #: 30248. OUR ORGANIZATIONAL STRUCTURE AND CERTIFICATION COMPLIES WITH (EN 10204-3.1.B). OUR FITTINGS SATISFY THE MATERIAL REQUIREMENT OF (PED 97/23-EC ANNEX 1-4.3

Heat Code: P477 Grade WPB

Page 5 of 17





Mgr. Quality Assurance