## CERTIFIED MATERIAL TEST REPORT

Tube Forgings of America, Inc. 5200 NW Front Avenue Portland, OR 97210 ISO 9001-2000 Certified

8/18/2005

Sold To: PLESA ANÁHUAC y CÍAS, S.A. de C.V.

AV. VALLE DE LAS ALAMEDAS NO. 66-A

TULTITLAN, EDO., MEX. C. P.54940

TFA Sales Order:

133086

Customer ID:

38350 103

Customer PO Reference: Attention To:

Ship To:

SPECIALISTS IN TRANSIT FORWARDING

1801 MARKLEY MODERN INDUSTRIAL PA

LAREDO, TX 78041

N667

Grade:

WPB 20007

TFA Part ID: Description:

TFA Heat Code:

3 STD CAP 1

Quantity:

Mill: Mill Heat:

**IPSCO** E4F125

Process:

WPB-CN3P

Test Bar Type: Yield (PSI): Tensile (PSI):

ROUND 40700 63100 29.00

% Elong In 4D B.H.N. :

Tensile Orientation:

**TRANS** 

Customer Part ID:

	C	MN	P	S	SI	МО	CR	NI	CU	V	СВ	В	TI	AL	C.E.
L	0.160	0.900	0.013	0.013	0.170	0.020	0.110	0.110	0.250	0.010	0.010	0.0005	0.0200	0.0130	0.36

Coupon Size:	Ft. Lbs	% Shear	Lateral Expansion (Mils)
Charpy V notch test at degrees F:	1:	1:	1:
Charpy Orientation:	2:	2:	2:
Charpy Orientation.	3:	3:	3:
	Avg:	Avg:	

1. THESE FITTINGS WERE NORMALIZED AT 1650F AND AIR COOLED. 2. THE STARTING MATERIAL IS PLATE WHICH IS SEAMLESS. 3. THE HARDNESS DOES NOT EXCEED 197BHN PART TO PART. 4. THIS PRODUCT IS SEAMLESS.

THE MATERIAL IS MANUFACTURED TO ASTM A 234 GR WPB REV: 03. ALSO PER ASME SEC II SA 234 GR WPB,2001 EDITION THRU ALL ADDENDAS AT TIME OF ORDER. 2. DESIGN AND DIMENSIONS TO ASME B16.9-2003 OR MSS-SP-75-98 AS APPLICABLE BY DESIGN. 3.PER NACE MR-01-75, 2003 REVISION. OUR QUALITY SYSTEM HAS BEEN REGISTERED BY ( ABS) TO (ISO-9001. REV: 2000), CERTIFICATE #: 30248. OUR ORGANIZATIONAL STRUCTURE AND CERTIFICATION COMPLIES WITH (EN 10204-3.1.B). OUR FITTINGS SATISFY THE MATERIAL REQUIREMENT OF (PED 97/23-EC ANNEX 1-4.3 ).

Heat Code: N667 Grade WPB

Page 3 of 17





John Peachey, Mgr. Quality Assurance