CERTIFIED MATERIAL TEST REPORT

Tube Forgings of America, Inc. 5200 NW Front Avenue

Portland, OR 97210 ISO 9001-2000 Certified

8/18/2005

Sold To: PLESA ANÁHUAC y CÍAS, S.A. de C.V.

AV. VALLE DE LAS ALAMEDAS NO. 66-A TULTITLAN, EDO., MEX. C. P.54940

Customer ID: **Customer PO Reference:** 133086 38350 103

Attention To:

TFA Sales Order:

Ship To:

SPECIALISTS IN TRANSIT FORWARDING

1801 MARKLEY MODERN INDUSTRIAL PA

LAREDO, TX 78041

Test Bar Type:

ROUND

TFA Heat Code: Grade: TFA Part ID:

P574 WPB 20009

Yield (PSI): Tensile (PSI): 56400 80900 25.00

Description: Quantity:

4 STD CAP 1

% Elong In 4D B.H.N.:

TRANS

Mill: Mill Heat: B4T6489 Process: WPB-C43

NUCOR Tensile Orientation:

Customer Part ID:

С	MN	P	S	SI	МО	CR	NI	CU	V	СВ	В	TI	AL	C.E.
0.177	1.070	0.007	0.006	0.170	0.010	0.020	0.040	0.110	0.010	0.010	0.0005	0.0100	0.0120	0.37

Coupon Size:	Ft. Lbs	% Shear	Lateral Expansion (Mils)
Charpy V notch test at	1.	4	1 -
degrees F:	1:	1:	1:
Charpy Orientation:	2:	2:	2:
	3:	3:	3:
	Avg:	Avo	

1. THESE FITTINGS WERE COLD FORMED AND STRESS RELIEVED AT 1225F AND AIR COOLED, 2. THE HARDNESS DOES NOT EXCEED 197 BHN PART TO PART. 3. STARTING MATERIAL IS PLATE. 4. THIS PRODUCT IS SEAMLESS.

THE MATERIAL IS MANUFACTURED TO ASTM A 234 GR WPB REV: 05. ALSO PER ASME SEC II SA 234 GR WPB,2004 EDITION THRU ALL ADDENDAS AT TIME OF ORDER. 2. DESIGN AND DIMENSIONS TO ASME B16.9-2003 OR MSS-SP-75-04 AS APPLICABLE BY DESIGN. 3.PER NACE MR-01-75, 2003 REVISION. OUR QUALITY SYSTEM HAS BEEN REGISTERED BY (ABS) TO (ISO-9001. REV: 2000), CERTIFICATE #: 30248. OUR ORGANIZATIONAL STRUCTURE AND CERTIFICATION COMPLIES WITH (EN 10204-3.1.B). OUR FITTINGS SATISFY THE MATERIAL REQUIREMENT OF (PED 97/23-EC ANNEX 1-4.3).

Heat Code: P574 Grade WPB

Page 4 of 17





John Peachey, Mgr. Quality Assurance